

DROSERA MS



Machine tools



High performance multifunctional zinc free oils for machine tools.

APPLICATIONS

DROSERA MS offers a wide range of products for all parts of machine tools (hydraulics, slides, gears).

- Machine tool slide ways under all conditions of speed and load (grades 68 to 320).
- Hydraulic circuits for hydraulic pumps and motors (grades 32 and 46).
- Gear boxes and feed mechanisms of all types with or without wet electro magnetic clutches (grades 68 to 320).
- High speed machine spindles (grades 5, 10, 15 and 22) and very high speed (grade 2).
- Hydrodynamic lubrication of mill roll stands during grinding (VG 460).
- Particularly suitable for centralized lubrication systems.
- ISO VG 68 to 150 are also well suited to cold heading applications.

SPECIFICATIONS

- ISO 6743/2 : FD2 ; FD5 ; FD10 ; FD 22 ; FD 32
- ISO 6743/4 : HG32
- ISO 6743/13 : GA68 ; GA100 ; GA150 ; GA220
- DIN 51502 : CGLP46 ; CGLP68 ; CGLP100 ; CGLP150 ; CGLP220 ; CGLP320 ; CGLP 460
- CINCINNATI MACHINE : P65-P62-P47-P50-P53-P45.

ADVANTAGES

- Excellent extreme-pressure properties
- Excellent anti-stick-slip properties.
- Strong stickiness grades (ISO VG 68 to 320).
- Very low coefficient of friction.
- Antioilmist properties.
- Very good foaming resistance.
- Very good oxidation resistance
- Very good protection against rust
- Very good anti-wear properties.
- Good filterability.

TYPICAL CHARACTERISTICS	METHODS	UNITS	DROSERA MS												
			2	5	10	15	22	32	46	68	100	150	220	320	460
Density at 15 °C	ISO 3675	kg/m ³	824	818	841	843	864	870	880	885	886	890	900	900	905
Viscosity at 40°C	ISO 3104	mm ² /s	2	5	10	15	22	32	46	68	100	150	220	320	460
Viscosity index	ISO 2909	-	-	-	85	100	100	104	104	103	100	99	99	98	95
Flash point Cleveland	ISO 2592	°C	82	150	160	190	210	210	230	240	250	260	260	260	260
Pour point	ISO 3016	°C	- 60	- 30	- 36	- 27	- 27	- 21	- 18	- 15	- 15	- 15	- 12	- 9	- 6
Aniline point	ISO 2977	°C	69	93	95	96	97	100	102	103	109	110	110	110	110

Above characteristics are mean values given as an information.

TOTAL LUBRIFIANTS
INDUSTRIE
05-06-2018 (supersedes 05-06-2012)
DROSERA MS
1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.